

## C 30 S

### 1) Product Description:

This is a PP homopolymer with a good flow properties and is particularly suitable for the extrusion of film yarn, monofilament, cast film and sheet.

### 2) Applications:

- Baler twines, packaging twines and ropes.
- Brush and broom filling and technical applications.

### 3) Typical data

Property	Unit	Typical Value	Test Method
MFI	Dg/min	6	ISO 1133
Density	g/cm <sup>3</sup>	0.9	ISO 1183
Flexural Modulus	N/mm <sup>2</sup>	1500	ISO 178
Tensile	N/mm <sup>2</sup>	34	ISO R527
Elongation	%	13	ISO R527
Izod Impact	Kj/m <sup>2</sup>	4	ISO 180
Hardness	point	71	ISO 868
Vicat	°C	155	ISO 306/A
H.D.T	°C	119	ISO 75/B

\*Typical Values : not to be construed as specifications

Producer: Marun Petrochemical Co.

Licensor: Basell

Packing: 25 Kg plastic bag