

“STEPS” CHINA

EXPANDABLE POLYSTYRENE

| Spec | Diam. Range (mm) | Times | Density (g/L) |
|-------------|-------------------------|--------------|----------------------|
| EPS E-301 | 1.0-1.6 | 70-85 | 12-14 |
| EPS E-302 | 0.85-1.25 | 60-70 | 14-16 |
| EPS E-303 | 0.7-0.9 | 55-65 | 15-18 |
| EPS E-401 | 0.5-0.8 | 40-55 | 18-25 |
| EPS E-501 | 0.4-0.6 | 30-40 | 25-30 |
| EPS P-301 | 1.0-1.6 | 75-90 | 11-13 |
| EPS P-302 | 0.85-1.25 | 65-75 | 13-15 |
| EPS P-303 | 0.7-0.9 | 55-70 | 14-18 |
| EPS P-401 | 0.5-0.8 | 45-55 | 18-20 |
| EPS P-501 | 0.4-0.6 | 40-50 | 20-25 |
| EPS F-301 | 1.0-1.6 | 70-85 | 12-14 |
| EPS F-302 | 0.85-1.25 | 60-70 | 14-16 |
| EPS F-303 | 0.7-0.9 | 50-65 | 15-18 |
| EPS F-401 | 0.5-0.8 | 40-50 | 18-25 |
| EPS F-501 | 0.4-0.6 | 30-45 | 25-30 |